

TEST REPORT

Number : HGHT06337967

Applicant : SHAOXING IDEAL TEXTILE CLOTHING CO., LTD
RM2102, NO.1 FUSHEN MANSION, DIDANG NEW
CITY, SHAOXING CITY, ZHEJIANG PROVINCE,
CHINA
Attn : LI MING

Date : Dec 07, 2019

Sample Description As Declared :


No. Of Sample : One (1)
Fibre Content : 100% Polyester
Material : Knitted Fabric
Finishing : -
End Uses : Upholstery
Colour : Green
Style No. : UNO
Order No./PO No. : -
Buyer's Name : -
Manufacturer's Name : -
Ref. : -

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : Dec 02, 2019

Prepared And Checked By:
For Intertek Testing Services Ltd., Hangzhou



Vivian Zhao
Manager



Intertek Testing Services Ltd., Shanghai, Hangzhou Branch

2-4,6F, of Block 6, No. 1180, Bin'an Road, High&New Tech Zone (Binjiang), Hangzhou 310052, China

上海天祥质量技术服务有限公司杭州分公司

中国杭州高新区(滨江)滨安路 1180 号 6 号楼 2-4,6 层 邮编:310052

Tel: +86 571 8768 8218 Fax: +86 571 8679 0296

E-mail: hztml@intertek.com

Attention is drawn to the terms and conditions on Website:

www.intertek.com.cn/responsibility

TEST REPORT

Number : HGHT06337967

Conclusion:


Color Fastness To Crocking	M
Color Fastness To Light	#
Pilling Resistance As Received	#
Bursting Strength As Received	M
Snagging Resistance	F
Abrasion Resistance	#

Note : M = Commercially Acceptable
N/A = Not Applicable

F = Fail

= No Comment

Prepared And Checked By:
For Intertek Testing Services Ltd., Hangzhou



Vivian Zhao
Manager



TEST REPORT

Number : HGHT06337967

Tests Conducted (As Requested By The Applicant)

1 Color Fastness To Crocking (AATCC 8-2016):

Dry	4.5
Wet	4.5

2 Color Fastness To Light (AATCC 16.3-2014, Option 3, Xenon-Arc Lamp):

<u>40 AATCC Fading Unit (AFU) Exposure</u>	
Grade	4.5

3 Pilling Resistance As Received (ASTM D3512/D3512M-16, Random Tumbler):

<u>After A 30-Minute Test</u>	
Rating	4.0

Remark : Viewing Option - ASTM Lightbox

4 Bursting Strength As Received (ASTM D3786/D3786M-18, Mullen Type Burster):

Over 80.0 lbf/in²

5 Snagging Resistance (ASTM D3939/D3939M-2013 (R2017), 600 Revolutions Test In ICI Mace Snag Tester):

<u>Along Wales</u>	
Rating	2.0

<u>Along Courses</u>	
Rating	2.0

Overall Average Rating	2.0
------------------------	-----

Remark: Visual Rating Standards: ICI Photographic Snagging Standards.

TEST REPORT

Number : HGHT06337967

Tests Conducted (As Requested By The Applicant)

6 Abrasion Resistance (ASTM D4966-12(2016), Option 1, Martindale Abrasion And Pilling Tester, 12 kPa Total Pressure):

Resistance

Face Side

80,000 Rubs

End of Report

Remark: This statement of conformity is only based on the actual measured test result by the laboratory, without taking the influence of uncertainty into account.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.